Reverse Neo Process

IRVINE SENSORS CORPORATION



1c) Apply field metal

1d) Apply photoresist

1e) Gold electroplate

1f) Strip photoresist & field metal etch



Reverse Neo Process

IRVINE SENSORS CORPORATION



1g) Apply polyimide

1h) Apply photoresist

1i) Image & develop photoresist & polyimide

1j) Strip photoresist & cure polyimide

Reverse Neo Process

IRVINE SENSORS CORPORATION



1k) Apply field metal

1l) Apply photoresist

1m) Image & develop photoresist. Gold electroplate

1n) Strip photoresist & field metal etch

NOTE: For additional layers, steps 1g through 1n are repeated.

Reverse Neo Process

IRVINE SENSORS CORPORATION

Solder Bumping Of Die

Fig 2a



Fig 2b



Fig. 2c



2a) Retrieve die

2b) Apply underbump metalurgy

2c) Apply solder bump



2c

Reverse Neo Process

IRVINE SENSORS CORPORATION

Flip-Chip Bonding

Fig. 3a



3a) Flip chip bumped die to substrate

Reverse Neo Process

IRVINE SENSORS CORPORATION



Fig 3b

Fig 3c

3b) Underfill die

3c) Pot die

Reverse Neo Process

IRVINE SENSORS CORPORATION



Fig. 3d

Fig 3e

Fig 3f

3d) Thin wafer

3e) Release wafer from aluminum substrate

3f) Mask wafer for test pad etch



Reverse Neo Process

IRVINE SENSORS CORPORATION

Fig 3g



Fig 3h



Fig 3i



3g) Etch polyimide to expose test pads

3h) Remove etch mask & test wafer

3i) Dice wafer

High Volume Reverse NEO Process

#1) Wafer Built Up Assembly



General Process Steps

1) Screen Print Electrically Conductive Epoxy on Built-Up Laminate Substrates
2) Place Flip Chip Devices
3) Cure Epoxy
4) Underfill Devices
5) Xfer. Mold Devices

High Volume Reverse NEO Process

Fig. 4b

2) Stacked Wafer Strip Assembly



General Process Steps

6) Release Carrier Film from Substrate (If Required)
7) Attach Memory and ASIC Wafers
8) Cut/Saw Wafers to Strips

Fig. 4c

3) Stacked Wafer Strip Assembly



General Process Steps

9) Interconnect or Bus Wafers by Metallizing Wafer Stacks

High Volume Reverse NEO Process

4) Thinned and Sawed Assembly

Fig. 4d



5) Thinned and Sawed Assembly

Fig. 4e



General Process Steps

10) Thin Stack Assembly

General Process Steps

11) Solder Bump Stack
12) Singulate (Saw) into Individual Stacks